

S355J2	≤16	355	≤3	510-680	3-40	22/20	≤150			27
	16-40	345	3-100	470-630	40-63	21/19	150-250			27
	40-63	335	100-400	450-600	63-100	20/18	250-400			27
	63-80	325			100-150	18/18				
	80-100	315			150-400	17/17				
	100-400	295-265								
Terased löögisitkuse äranäitamise										
S355K2	≤16	355	≤3	510-680	3-40	22/20	≤150			40
	16-40	345	3-100	470-630	40-63	21/19	150-250			33
	40-63	335	100-400	450-600	63-100	20/18	250-400			33
	63-80	325			100-150	18/18				
	80-100	315			150-400	17/17				
	100-400	295-265								
S450JO	≤16	450	3-100	550-720	3-40	20/17	≤150		27	
	16-40	430	100-150	530-700	40-63	19/17				
	40-63	410			63-100	18/17				
	63-80	390			100-150	18/17				
	80-100	380			150-250	-				
Terased löögisitkust näitamata										
S185	≤16	185	≤3	310-540	3-40	18/16				
	16-100	175	3-100	290-510	40-63	17/15			-	
	100-150	165	100-150	280-500	63-100	16/14				
	150-250	155-145	150-250	270-290	100-150	15/13				
					150-250	15/13				
E295	≤16	295	≤3	490-660	3-40	20/18				
	16-40	285	3-100	470-610	40-63	19/17			-	
	40-63	275	100-150	450-610	63-100	18/16				
	63-80	265	150-250	440-610	100-150	16/15				
	80-100	255			150-250	15/14				
	100-250	245-225								
E335	≤16	335	≤3	590-770	3-40	16/14				
	16-40	325	3-100	570-710	40-63	15/13			-	
	40-63	315	100-150	550-710	63-100	14/12				
	63-80	305	150-250	540-710	100-150	12/11				
	80-100	295			150-250	11/10				
	100-250	275-255								
E360	≤16	360	≤3	690-900	3-40	11/10				
	16-40	355	3-100	670-830	40-63	10/9			-	
	40-63	345	100-150	650-830	63-100	9/8				
	63-80	335	150-250	640-830	100-150	8/7				
	80-100	325			150-250	7/6				
	100-250	305-285								

1) vahemik sõltuvalt paksusest

2) standard toob ka A80

3) lugejas valtsimise (piki) suunas/nimetajas ristisuunas