

Betoonsarrusteraste margid ja keemiline koostis

T. EN10080

Margitähis	Elementidesisaldus %, max						Muud
	C	Si	Mn	P	S	N	
B500A	0,24	-	-	0,055	0,055	0,014	CEV≤0,52 (0,50) Cu0,8
B500B	(0,22)	-	-	(0,050)	(0,050)	(0,012)	
B450C							

¹⁾ sulgudes valuanalüüsi korral

